

Dulux AcraTex Prep Treat

AUDA0446

Part A	194-85771
--------	-----------

Product Overview

Previously known as DULUX AcraTex Prep Treat
DULUX AcraTex Prep Treat water based low toxicity bacterial fungal and algal wash / sterilizing solution which will kill film spoilage species, making it an integral component with the 962 Roof Membrane System.

Features And Benefits

- Water based
- Kills mould spores
- Fast dry
- Easy application, clean up
- Effective that prevents recurrence of mould growth
- 2 Hour recoat

Uses And Typical Specifications

Uses DULUX AcraTex Prep Treat is a fungal and algal killer, applied to sound or weathered concrete roof tiles providing as a pretreatment for DULUX AcraTex 962 Roof Membrane .

Precautions And Limitations

Recommendations, permissible coverage rates & application temperature must be observed. DULUX AcraTex 500/10 Prep Treat must not be applied when rain is anticipated. Adequate protection must be given against rain and dust to the coating during application.


Do not apply to previously painted unless all previous coating has been removed.

Protect all plant life on the ground as any overspray will KILL all plant life.

Performance Guide

Weather	Not applicable	Salt	Not applicable
Heat Resistance	Not applicable	Water	Not applicable
Solvent	Not applicable	Abrasion	Not applicable
Acid	Not applicable	Alkali	Not applicable

Typical Properties

Clean Up	Clean up water Water																														
Application Method	 Air Spray																														
Application Conditions	<table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="text-align: left;">Solids By Volume</th> <th style="text-align: center;">2</th> <th></th> <th></th> <th></th> </tr> <tr> <th></th> <th style="text-align: center;">Min</th> <th style="text-align: center;">Max</th> <th colspan="2" style="text-align: center;">Recommended</th> </tr> </thead> <tbody> <tr> <td>Wet Film Per Coat (microns)</td> <td style="text-align: center;">0</td> <td style="text-align: center;">0</td> <td colspan="2" style="text-align: center;">0</td> </tr> <tr> <td>Dry Film Per Coat (microns)</td> <td style="text-align: center;">0</td> <td style="text-align: center;">0</td> <td colspan="2" style="text-align: center;">0</td> </tr> <tr> <td>Recoat Time (min)</td> <td style="text-align: center;">4Hours</td> <td style="text-align: center;">NA</td> <td colspan="2"></td> </tr> <tr> <td>Theoretical Spread Rate (m²/L)</td> <td></td> <td></td> <td colspan="2" style="text-align: center;">12</td> </tr> </tbody> </table>	Solids By Volume	2					Min	Max	Recommended		Wet Film Per Coat (microns)	0	0	0		Dry Film Per Coat (microns)	0	0	0		Recoat Time (min)	4Hours	NA			Theoretical Spread Rate (m ² /L)			12	
Solids By Volume	2																														
	Min	Max	Recommended																												
Wet Film Per Coat (microns)	0	0	0																												
Dry Film Per Coat (microns)	0	0	0																												
Recoat Time (min)	4Hours	NA																													
Theoretical Spread Rate (m ² /L)			12																												

Application Guide

Surface Preparation	<ul style="list-style-type: none"> SYSTEM INFORMATION AND EQUIPMENT <p>The DULUX AcraTex 962 Roof Membrane system comprises of substrate cleaning and preparation, consolidating primer relevant to substrate condition, followed by 2 coats (minimum) of DULUX AcraTex 962 Roof Membrane.</p> <p>Pay particular attention to the lip area of the concrete tile as this area is mostly prone to build up areas of mould and algal growth.</p>
Application Procedure And Equipment	<ul style="list-style-type: none"> APPLICATION PROCEDURE AND EQUIPMENT <p>Product should be thoroughly mixed before use. Refer to the DULUX AcraTex Application Manual for detailed application instructions. Apply DULUX AcraTex Prep Treat liberally to problem surface via garden pressure spray unit.</p> <p>Let set for 24 hours for optimum results.</p> <p>Remove any dead debris by scrubbing with a stiff bristle brush or using a garden hose with nozzle at maximum velocity.</p> <p>Allow surface to dry completely before applying the correct primer/sealer then DULUX AcraTex 962 Roof Membrane.</p> <p>PRACTICAL COVERAGE AT RECOMMENDED FILM THICKNESS A spread rate of 12.00 sq. meters per litre corresponds to 0 microns dry film thickness assuming no loss. Practical spreading rates will vary due to such factors as method and conditions of application and surface roughness.</p> <p>Apply a 2nd coat prior to painting for increased protection. Allow to dry.</p> <ul style="list-style-type: none"> As the surface area of a "profiled roof" is greater than equivalent flat roof surface, additional material should be allowed for. All plant life should be covered when using this product. Garden pressure atomiser

Health And Safety

MSDS Number	5506	Health Effects	For detailed information refer to product Material Safety Data Sheet available through Dulux Sales and Customer Service offices 132377 AUS. For detailed information refer to product Material Safety Data Sheet available through Dulux Sales and Customer Service offices 132377 AUS.
Protective Equipment	Avoid any skin contact and inhaling spray mist. Use in well ventilated areas. Always use overalls, safety shoes, safety mask or respirator, safety glasses and safety gloves	Storage	0

In the case of emergency, please call 1800 033 111

Transport And Storage

Pack A	194-85771	Shipment Name	Not dangerous goods; No special transport requirements
Size	15 Litre	Weight	16.5 Kg
Flash Point	NA	UN Number	NA
Dangerous Goods Class	NA	Package Group	NA

Images



Disclaimer

Dulux and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating systems.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (Australia) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "AcraTex" and Other marks followed by ® are registered trademarks of DuluxGroup (Australia) Pty Ltd ABN 67 000 049 427. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton, Victoria 3168 AU ABN 67 000 049 427